RG104 E-1 Box 121

1880

Weekly Report of Silver Purchases and Deposits Melted at United States Mint.

Date.	Assay No.	Name of Depositor.	Weight before Melting. Oz.	Dec.	Weight after Melting. Oz.	Dec.	Loss. Oz.	Dec.	Loss per ct.	Gain. Oz.	Dec.	Description of Bullion.	Notes of Melter and Refiner.
May 17th	217	G. C. Thompson	38 80		38 65			15	38			Bar, Stick Cases, &c.	2/6/80.
	8	Paul Schmelick	135 15		134 85			30	24			For. Coin	The deposits are from the following sources:
19th	9	G. C. Thompson	106 80		106 60			20	19			Spoons, Forks, &c.	
31st	20	do	38 35		38 20			15	39			U.S. & For. Coin	8 of Plate with a fair wastage of 0.44 %: —
	1	John H. Platt, Cash'r	108 25		108 05			20	19			U.S. & For. Coin	
22d	2	G. C. Thompson	44 90		44 75			15	33			For. Coin	5 of Coin with an average, a shade fuller than usual of 0.27 %: —
	3	do	647 45		606 20		41	25	638			Bar & Gold	
			1109 70		1067 30		42	40	382				3 of bars, base coin and Lake grains, with a reasonable wastage of 5.17 %.
													1 of N.Y. Assay Office
													17 Total.

Transferred to Bullion fund during the week 101,223.90 Oz, Newark Bars; 6069.20 Oz, St. Louis; 34,163 Oz, Pennsylvania Lead Company; 13,088.95 Oz, Platt and 28,183.70 Oz, U.S.A.O.N.Y.

For week ending May 22d 1880.

Date.	Assay No.	Name of Depositor.	Weight before Melting. Oz.	Dec.	Weight after Melting. Oz.	Dec.	Loss. Oz.	Dec.	Loss per ct.	Gain. Oz.	Dec.	Description of Bullion.	Notes of Melter and Refiner.
May 24th	224	G. C. Thompson	100 15		99 80			35	35			Spoons, Stick Cases, &c.	J. H. C. Booth M. & R.
	5	Snyder, Harris, Bassett & Co.	91 85		91 65			20	22			For. Coin	
	6	John Patton	250 80		250 50			30	12			Spoons, Pl. &c.	
	7	G. C. Thompson	237 25		233 30		3	95	167			Pl. Spoons, &c.	
26th	8	J. N. Clark	121 35		121 05			30	25			Bar & Button & Gold	
27th	9	G. C. Thompson	68 70		68 40			30	43			Forks, Spoons, &c.	
	30	do	283 60		283 30			30	11			Bars, Ring, &c.	
	1	Sailer & Stevenson	1071 50		1071 50							Bars, U.S.A.O.N.Y.	
	2	A. H. Lyon	450 40		447 75		2	65	589			For. Coin & Some Counter.	
28th	3	G. C. Thompson	102 80		99 45		3	35	325			Cases, Spoons, &c. & Spoons, &c. Specimens, Stick.	
			2778 40		2766 70		11	70	69				

Transferred to Bullion fund during the week 5,453 Oz, Boston & Colorado Bars; 32,379.50 Oz, St. Louis; 98,638.10 Oz, Newark; 19,118.80 Oz, Platt; 34,759.70 Oz Pennsylvania Lead Company; 4,080.50 Oz, U.S.A.O.N.Y., and Foreign Coin which weighed 1,998.30 Oz. before melting and 1,996.15 after.

For week ending May 29th 1880.

S. Nobley Dingman
Register

RG104 E-1 Box 121

Return of Silver Purchases
& Bullion Deposits melted
for weeks ending: —

May 22nd 1880

May 29th 1880

NARA RG104, Entry 1, Box 121

[Abstract:] Report of Silver Purchases & Deposits melted for weeks ending: -

May 22, 1880
May 29, 1880

Weekly Report of Silver Purchases and Deposits Melted at United States Mint.

[Please see original images for data table.]